Endot. The source for plenum & riser raceways

More sizes, and more flexible than any other! You can always count on Endot for the widest selection and easiest-to-use products. Whether you're looking for plenum or riser raceway, look for the Endot name to be sure you're getting the best available.

ENDOCOR/PL Plenum raceway

ENDOCOR/RI Riser raceway

- Pre-installed pull line in all sizes.
- Super flexible never brittle and will not kink.
- Available in lengths from small hand coils to master reels.
- Plenum & riser available in orange and white. Other colors available on Special Order.
- UL Listed.

- Meets requirements of NEC 2002, Section 770 and 800.
 Both are available in sizes: 1/2", 3/4", 1", 1 1/4", 1 1/2", and 2".
 Our plenum raceway is corrugated, non-metallic, and produced from PVDF resin.
- Our riser raceway is corrugated, non-metallic and non-halogenated.

Available through distributors throughout the U.S. and Canada; call for the one nearest you.

Endot Industries, Inc., 60 Green Pond Road, Rockaway, NJ 07866 http://www.endot.com • e-mail: info@endot.com

1-800-44-ENDOT

ENDOCOR/PL AND ENDOCOR/RI

SPECIFICATIONS

| | PART NUMBER* PL=Plenum / Rl=riser | SIZE | NOMINAL ID | NOMINAL OD | |
|---------------------------|--|--|--|--|--|
| NOMINAL DIMENSIONS* | IPR 050 / IRI 050 IPR 075 / IRI 075 IPR 100 / IRI 100 IPR 125 / IRI 125 IPR 150 / IRI 150 IPR 200 / IRI 200 | 1/2" 3/4" 1" 1-1/4" 1-1/2" 2" | 0.650" ID 0.870" ID 1.100" ID 1.250" ID 1.500" ID 2.000" ID | 0.850" OD 1.125" OD 1.350" OD 1.600" OD 1.870" OD 2.400" OD | |
| DESIGN | CORRUGATED - for f | CORRUGATED - for flexibility | | | |
| MATERIAL | ENDOCOR/PL ENDOCOR/RI | PVDF resin Nylon resin | | | |
| PACKAGING | HAND COILS of 250 ft. & 500 ft. REEL LENGTHS of 1,000 ft. or longer | | | | |
| PULL LINE or CABLE | Pre-installed Kevlar pull tape or cable (up to 7/16") in diameter | | | | |

^{*}Partial Number - does not include reel, pull line, color etc. See Part Number Chart for complete part number.

| ENDOCOR/PL | | | | | |
|--------------------------------|--------------------|----------|--|--|--|
| ACCEPTANCE CRITERIA | TEST METHOD | VALUE | | | |
| UL STANDARD 2024 (UL Test 910) | | | | | |
| Maximum Flame Propagation | UL 2024, sec.8 | 1.50 ft. | | | |
| Peak Optical Smoke Density | UL 2024, sec.8 | 0.06 | | | |
| Average Optical Smoke Density | UL 2024, sec.8 | 0.01 | | | |
| FIRE RESISTANCE | | | | | |
| Oxygen Index | ASTM D2863 | 63% | | | |
| Flame Rating | ASTM D2863 | S-E | | | |
| UL Classification | UL 94 | V-O | | | |
| | | | | | |

ASTM D149 ASTM D150

Note: The use of Plenum Raceway does not eliminate the need for Plenum rated cable.

| ENDOCOR/RI | | | | | |
|---------------------------------|----------------|-----------|--|--|--|
| ACCEPTANCE CRITERIA | TEST METHOD | VALUE | | | |
| UL STANDARD 2024 (UL Test 1666) | | | | | |
| Maximum Flame Propagation | UL 2024, sec.9 | 4.25 ft. | | | |
| Maximum Damage Height | UL 2024, sec.9 | 6.75 ft. | | | |
| MECHANICAL PROPERTIES | | | | | |
| Tensile Strength, Yield | ASTM D638 | 7,800 PSI | | | |
| Flexural Strength | ASTM D790 | 9,200 PSI | | | |
| THERMAL PROPERTIES | | | | | |
| Melting Point | ASTM D789 | 420° F | | | |

Note: The use of Riser Raceway does not eliminate the need for Riser rated cable.



CORPORATE HEADQUARTERS

ELECTRICAL PROPERTIES

Dielectric Constant @ 5 MHz

Dielectric Strength

60 Green Pond Road Rockaway, NJ 07866 800-443-6368 • FAX 973-625-4087

ENDOT INDUSTRIES, INC.

www.endot.com • e-mail: info@endot.com

PLANT LOCATIONS

541 V/mil

5.2

Greeneville, TN Pryor Creek, OK