



ENDOT INDUSTRIES, INC.

PIPE AND TUBING • DUCT AND INNERDUCT

HEAT FUSION OF ENDOT PE 4710 PIPE & TUBING

Endot Industries recommends using the times and temperatures listed below for the heat fusion of Endot pipe to other pipe or fittings produced from PE 4710 material. The actual times may need to be adjusted for varying weather conditions such as wind, rain, cold or heat, etc.

HEAT FUSION TIME FOR PE 4710 PIPE AND TUBING AT A TEMPERATURE OF 500° F

TIME IN SECONDS

SIZE	BUTT FUSION	COOLING TIME	SOCKET FUSION	COOLING TIME
CTS				
3/4"	8 - 10	50	9 - 10	30
1"	14 - 17	50	11 - 13	30
1-1/4"	16 - 19	50	14 - 16	30
1-1/2"	18 - 21	60	16 - 18	40
2"	22 - 25	60	18 - 20	40
IPS				
1/2"	8 - 10	50	9 - 10	30
3/4"	14 - 16	50	12 - 14	30
1"	16 - 19	50	15 - 17	40
1-1/4"	18 - 21	70	17 - 20	40
1-1/2"	24 - 30	90	20 - 23	40
2"	30 - 34	90	24 - 27	40

CAUTION: Excessive heating times can over heat the pipe or fitting and result in brittle joints. Shortened heating times can result in an incomplete bond of materials and a weak joint that may fail.

CORPORATE HEADQUARTERS

60 Green Pond Road
Rockaway, NJ 07866
800 443 6368 – FAX 973 625 4087 www.endot.com - e-mail info@endot.com

PLANT LOCATIONS

South Point, OH
Greenville, TN
Pryor Creek, OK